

EMBLEM Solvent Value WhiteBack

EMBLEM SOVWB is a matt to matt white paper. It is useful for large format printing with solvent-latex- and uv curable inks.

Matchcode: SOVWB

Material: waterresistant one-sided coated Paper

Finish: matt
Colour: white

Weight: 150 g/m^2 Thickness: 180 µm

Opacity dry: 99 % acc. ISO 2471

Whiteness: 103 % acc. ISO 14475

Fire behaviour: n.n

Standard roll width: 42", 50", 54", 60", 63", 72", 126"

Standard roll length: 100 m

COMPATIBLE INKS:

Eco solvent: no UVC: yes Solvent: yes Latex: yes

Different printers, inks, resolutions and printing qualities result into numerous different printing parameters. In addition, there a numerous factors influencing processing and the application of our materials. For this reason, we cannot make specific statements as to drying times and maximum ink absorption. For this reason, we recommend you to perform own tests in order to verify the desired results. Our product specifications are not to be understood as legally binding guarantees assuring specific characteristics. Any liabilities and guarantees, as well as claims for compensation beyond the value of the product itself are excluded.





EMBLEM Solvent Value WhiteBack

Description:

EMBLEM SOVWB is a matt to matt white paper. It is useful for large format printing with solvent- latex- and uv curable inks. The finish is especially made for billboard application with high opacity and specific surface. To get best print quality we recommend to use ICC calibration files with your RIP. Be careful not to damage the coating when folding the paper. We do not recommend to roll the paper because this could cause problems fixing the poster to the billboard.

Processing:

Before mounting it is advisable to soak the prints with water for about 15 minutes and keep it wet until application within 72 hours.

For best application we recommend original glue like Bacocell from Bacoplac or UST 2500N Zelura from Henkel. Please follow the special instructions of the supplier of the glue. Additives like frost protections or bactericides should be used from the same supplier who is used for the glue. It is necessary to make his own tests with this combinations of materials. The printed side has to be clean from glue and has to be cleaned if necessary. Applikation with direct solar radiation could cause problems with release the paper, because the drying speed of the paper could be too high.

Application:

Poster, POS, Citylights